



ProFLOW 3000

Product Description

ProFLOW Resins are high flow rate (MFR 1500+) polypropylene resins that quickly melt to low viscosity Newtonian fluids.

General

Material Status: Commercial: Active
Availability: Globally
Features: Semi Crystallinity/Low Velocity
Uses: Multiple
Processing Method: Injection Molding, Extrusion, Blown Film, Compounding

ASTM & ISO Properties

<u>Thermal</u>	<u>Nominal Value</u>	<u>Unit</u>	<u>Test Method</u>
Melting Point	142	°C	DSC
<u>Physical</u>	<u>Nominal Value</u>	<u>Unit</u>	<u>Test Method</u>
Density	0.92	g/cc	ISO 1183
Molding Shrinkage	N/A	N/A	N/A
<u>Mechanical</u>	<u>Nominal Value</u>	<u>Unit</u>	<u>Test Method</u>
Tensile Modulus	111,000	psi	ISO 527-2
Tensile Strength	3,700	psi	ISO 527-2
<u>Impact</u>	<u>Nominal Value</u>	<u>Unit</u>	<u>Test Method</u>
Notched Izod	0.32	ft-lb/in	ISO 180
<u>Rheological</u>	<u>Nominal Value</u>	<u>Unit</u>	<u>Test Method</u>
Melt Index	~1500	g/10 min	230°C, 0.0825" ID, 2.16 kg
Modified MFR	5.0-6.5	g/10 min	230°C, 0.0200" ID, 2.16 kg
Melt Viscosity	61	poise	190°C, 100 sec ⁻¹

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon conditions that purchasers shall make their own test to determine suitability of such products for their particular purposes and uses, and purchasers assume all risks and liability for the results of use of the products, including use in accordance with the seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the product described.