

DuraPET™ 0624GF30 PCR ST

Product Description

DuraPET™ is a modified PET material that demonstrates extreme high impact and wear characteristics due to glass fibers. It is a highly durable material that can withstand outdoor environmental conditions. It exhibits ductile failure as low as - 20°C.

General

Material Status: Commercial: Active
Availability: Globally
Features: Low Crystallinity/Extreme High Toughness
Uses: Multiple
Processing Method: Injection Molding, Extrusion, Thermoforming, Blown Film

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density	1.51	g/cc	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	11,100	psi	ASTM D638
Tensile Modulus	1,019,528	psi	ASTM D638
Flexural Modulus	965,200	psi	ASTM D790
Elongation @ Break	5.25	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Gardner Impact (23°C)	72	in-lb	ASTM D5420
Rheological	Nominal Value	Unit	Test Method
Melt Flow Rate (285°C, 2.16 Kg)	5	g/10 min	ASTM D1238

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon conditions that purchasers shall make their own test to determine suitability of such products for their particular purposes and uses, and purchasers assume all risks and liability for the results of use of the products, including use in accordance with the seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the product described.